FMS

fffff?f?????f?????ff?????

BALLISTIC TEST REPORT

DATE: 23/09/2007 **REPORT NO.:** 19038

CUSTOMER: LIOR **ORDER NO.:**

INVOICE NO.: **DATED:**

PANEL TYPE	ARAMID 234	**TEST STD.**	NIJ STD. 0101.04
PLY NO.	29	**Distance**	5 [m]
Weight [kg]	1.1 **Size [mm]** 400X400	**TEMP.**	23 [C^0]
Weight [kg/m2]	6.875	**Relative Humidity**	46 [%]

Remarks: in conjuction with 5mm foam + 1mm p.c

TEST REPORT

Clay Calib. [mm]	1	2	3	4	5	AVG.
	19	19	20	19	20	19.4

Test No.	Barrel Diameter [mm]	Round Type	Round Lot	Bullet Type	Bullet Weight [grain]	Velocity [m/s]	Velocity [ft/s]	Back Face [mm]	Stop / Penetrate	Shot Angle	Remarks
1	7.62	Tokarev	Chaina	S.J/L.C	85	509.63	1,672	19	STOP	0	
2	7.62	Tokarev	Chaina	S.J/L.C	85	508.71	1,669	19	STOP	0	
3	7.62	Tokarev	Chaina	S.J/L.C	85	509.32	1,671	20	STOP	0	
4	7.62	Tokarev	Chaina	S.J/L.C	85	511.45	1,678		STOP	30	
5	7.62	Tokarev	Chaina	S.J/L.C	85	511.15	1,677		STOP	30	
6	7.62	Tokarev	Chaina	S.J/L.C	85	508.71	1,669	20	STOP	0	
7											
8											
9											
10											
11											
12											

Remarks:

Approved by: Yaniv Montakyo
Manager
Ballistic Test Laboratory

コピー及び転載禁止
ラムエンタープライズ株式会社

Tel: +972-3-9223206
Fax: +972-3-9225414
Email: fms2@fms.co.il
Web: www.fms.co.il
P.O.Box: 18077
TEL-AVIV 61180
ISRAEL