

FMS

ENTERPRISES MIGUN LTD.

BALLISTIC TEST REPORT

DATE : 18/11/05 TEST NO. : 16554
CUSTOMER : LIOR. CODE :
SIZE : 400X400 PANEL WEIGHT sq.mtr: 5.395 kg.
TEMP. : 22.0 (deg.C) HUMIDITY : 56 %
RANGE : 5.0 mtr.
SPEC. : NIJ STD 0101.04 LEVEL : III-A
PANEL CONDITIONED : DRY

REMARKS:
23 LAYERS ARAMID 234.
102mm CLAY BACKING.

RESULTS TABLE

SHOT NO.	GUN MODEL	BARR. LENG. mm	CALIB -ER mm	BULLET TYPE	BULLET WEIGHT grain	SHOT ANGLE deg.	TRAUMA		VEL.		PENE TRAT Y/N	INCL. V-50 +/-
							DEPTH mm	WIDTH mm	mtr/ sec.	ft./ sec.		
1	BARREL	10.00	9.000	F.M.J.	124.0	0	27	0	440	1442	N	+
2	BARREL	10.00	9.000	F.M.J.	124.0	0	27	0	438	1438	N	+
3	BARREL	10.00	9.000	F.M.J.	124.0	0	0	0	436	1431	N	+
4	BARREL	10.00	9.000	F.M.J.	124.0	30	0	0	439	1439	N	+
5	BARREL	10.00	9.000	F.M.J.	124.0	30	0	0	436	1430	N	+
6	BARREL	10.00	9.000	F.M.J.	124.0	0	0	0	434	1425	N	+
AVERAGE OF NOT PENETRAT SHOTS							9.0	0.0	437	1434		0.0

GUNNER NAME : YUVAL FUCHS

INSPECTOR NAME :

Signature of gunner

Signature of inspector

