

H.P. WHITE LABORATORY, INC.

3114 Scarborough Road
Street, Maryland 21154-1822
Telephone: (410) 838-6550
Facsimile: (410) 838-2802
Email: info@hpwhite.com
www.hpwhite.com



13 June 2007
(HPWLI 10460-06B)
(Revised 27 June 2007)
(Revised 28 June 2007)

Lam Enterprise Co.
2-3-3 Horidome-Cho #904 Nihonbashi Chuo-ku
Tokyo Japan 103-0012

Gentlemen:

In accordance with your instructions, H.P. White Laboratory, Inc. conducted Ballistic Limit, Protection (V50BL[P]) testing of one transparent armor sample received 3 May 2007 via United States Postal Service.

Testing was conducted in accordance with your instructions, and the provisions of MIL-STD-662F, using caliber 7.62x25, 85 grain, steel jacket, lead core ammunition. The test sample was mounted on an indoor range 15.0 feet from the muzzle of a test barrel to produce zero degree obliquity impacts. Photoelectric lumiline screens were positioned at 5.0 and 10.0 feet which, in conjunction with elapsed time counters (chronographs), were used to compute projectile velocities 7.5 feet from the muzzle. Penetrations were determined by visual examination of a 0.020 inch thick aluminum alloy 2024-T3 witness panel positioned 6.0 inches behind, and parallel to, the test sample. Table I presents a summary of the enclosed data record.

TABLE I SUMMARY OF RESULTS

Test Sample			Ballistic Threat		Ballistic Limit (fps)		
Number	Weight (lbs.)	Thickness (in) (a)	Caliber	Shots Total/V50	V50 BL(P)	High Partial	Low Complete
GBS-3A-T (Vision Block)	13.16	1.248	7.62x25mm, SJLC	11/2	2138	2120	2157

(a) Average of four corner thicknesses.

This report is based on data obtained from having tested only the sample submitted, and should NOT be interpreted as an endorsement by H.P. White Laboratory, Inc. of the continuing quality, or performance, of any other items of the same, or similar, design.

The test sample will be returned via Federal Express. Should you have any questions regarding this matter, or if we may be of any further service, please do not hesitate to contact us.

Very truly yours,

H.P. White Laboratory, Inc.

Craig B. Dunn

CBD/tc
Enclosure